Revised January 2004



9411 Corsair Road Frankfort, IL 60423 1-800-552-0299 Phone 1-815-464-5650 Fax

**EMERGENCY PHONE 1-800-255-3924** 

# TECHNICAL DATA SHEETS MP 54460

## **Description:**

MP 54460 is a medium viscosity epoxy/copolymer resin formulation recommended for industrial bonding, small potting and laminating applications where excellent structural, mechanical and electrical properties are required. This two-part adhesive exhibits good wetting, cures at room temperature and develops strong, low shrinkage bonds to most materials including optical fibers, glass ceramics, most metals and many rigid plastics. It has excellent dimensional stability over a wide temperature range. Fully cured MP 54460 is a durable electrical insulator with good physical properties, plus resistance to water, weather, ozone and oxygen, petroleum solvents, lubricating oils, jet fuels, gasoline, alcohol, salt solutions, mild acids and alkalis and many other organic and inorganic compounds.

### **Typical Properties:**

All properties given are at 25°C unless otherwise noted.

Color		Off- White
Viscosity	Part A	40,000 cps
	Part B	80,000 cps
	Mixed	50,000 cps *
Specific Gravity	Part A	1.15
	Part B	1.07
	Mixed	1.12
Pot Life		20 minutes
Mass		50 grams
Hardness Shore - D		75 - 80
Temperature Range		-60 to 150°C
Tensile Elongation		2.35%
Tensile Strength		6600 psi
Tensile Lap Shear		3700 psi
(2024 T3 Aluminum		
Abraded / MEK W	/ipe)	
T-peel Strength		25 pli *
(Al to Al)		
Dielectric Constant		4.5 *
(25C, 100Hz)		
Dielectric Strength		440 v/mil *
Volume Resistivity		8 x 10 <sup>14</sup> ohm-cm *

### **MIX RATIO:**

Mix Ratio (Part A to B):
by weight 213 to 100
by volume 2 to 1

#### **CURE SCHEDULE:**

24 hours at 25°C or 2 hours @ 65°C

# **SHELF LIFE:**

12 Months

#### **INSTRUCTIONS:**

- 1) Bring to room temperature before use.
- Weigh and mix parts A and B accurately and thoroughly, scraping sides of container often. Pre-bleed side-by-side cartridges, discarding the first 3 inches of dispensed material. Maintain adequate velocity during dispensing to ensure complete mixing.
- 3) Allow to cure undisturbed.

# **Engineering Excellence**

For technical information and support call 1-800-552-0299 or visit our website at

